

Typical characteristic of GSM 55 are shown below:

<b>W/P 55 GSM</b>		
Grade		writing/printing
Basis Weight (g/m <sup>2</sup> )		55 ± 2%
Moisture (%)		5 – 6
Brightness (photovolt)		90 - 91
Opacity (%)		73 – 76
COBB value (30 sec)		18 – 21
Tensile (N/15mm)	MD	4 – 6
	CD	3 – 4
Tear (mN)	MD	≈ 400
	CD	≈ 480

- Designated reel width indicates a tolerance of ± 0.5%
- Average diameter of reel is 100 cm ± 2%
- All reel are packaged sea worthy packing (2-3 layers of stretch wrap, carton side discs)
- All reel have the following information writing on them: Company Name and Logo, Paper Machine #, Reel Serial Number, Substance (gsm), Size (cm), Grade Weight (kg), Shift Manager, Date of Production, Customer Name

These specifications are not part of a contract or any binding agreement; item specifications can be changed at any time by SPI without prior notice.