

Typical characteristic of GSM 100 are shown below:

W/P 100 GSM		
Grade		writing/printing
Basis Weight (g/m ²)		100 ± 3%
Moisture (%)		6 -- 6.5
Brightness (photovolt)		90 -- 92
Opacity (%)		85- 87
COBB value (30 sec)		25 – 28
Tensile (N/15mm)	MD	12 – 14
	CD	6 – 7
Tear (mN)	MD	≈ 500
	CD	≈ 600

- Designated reel width indicates a tolerance of ± 0.5%
- Average diameter of reel is 100 cm ± 2%
- All reel are packaged sea worthy packing (2-3 layers of stretch wrap, carton side discs)
- All reel have the following information writing on them: Company Name and Logo, Paper Machine #, Reel Serial Number, Substance (gsm), Size (cm), Grade Weight (kg), Shift Manager, Date of Production, Customer Name

These specifications are not part of a contract or any binding agreement; item specifications can be changed at any time by SPI without prior notice.